


LIEKKI<sup>®</sup> Er40-4/125 fiber is a highly doped erbium fiber designed for C- and L-band amplifiers, and ASE sources. Due to the high absorption level this fiber is particularly suited for L-band applications.



## **Features**

- Excellent batch consistency of erbium peak absorption and spectral shape
- Very short application length reduces non-linear effects like FWM, SRS and SBS
- Wide and flat spectrum
- Low polarization mode dispersion, typical value <25 fs/m</li>
- · Dual layer UV-cured acrylate coating
- Suitable for both 980 nm and 1480 nm pumping
- Telecom-like geometry with good spliceability to standard single mode fibers
- Telcordia GR-1312-CORE Generic Requirements qualified

## **Applications**

- L-band DWDM
- · L-band ASE sources
- · Low non-linearity applications
- LIDAR

## **Typical Fiber Specifications**

Fiber		LIEKKI <sup>®</sup> Er40-4/125
Optical	Units	
Mode Field Diameter at 1550 nm	μm	$6.5 \pm 0.5$
Peak Core Absorption at 1530 nm	dB/m	$40.0 \pm 4.0$
Core Numerical Aperture (nominal)		0.2
Cut-off Wavelength	nm	890 ± 90
Geometrical and mechanical		
Core Concentricity Error, ≤	μm	0.7
Cladding Diameter (flat-to-flat)	μm	125 ± 2
Cladding Geometry		Round
Coating Diameter		245 ± 15
Coating Material		Dual coated high index acrylate
Proof Test, ≥	kpsi	100

