
*n*LIGHT

LIEKKI[™] PASSIVE LARGE MODE AREA FIBERS



Applications

- Pigtails for fiber lasers and amplifiers
- All-fiber subassemblies
- High brightness power delivery
- Fiber based components for fiber lasers (e.g. pump combiners)

LIEKKITM passive fibers are especially designed and manufactured to match with commercially available large mode area active fibers such as LIEKKITM Yb1200 product line LMA fibers. The passive fibers are matched to the core diameters and numerical apertures of the active counterparts so that excellent beam guality is maintained throughout the fiber laser or amplifier.

LIEKKITM passive fibers are available in single cladding, double cladding (DC), single cladding polarization maintaining (PM) and double cladding polarization maintaining configuration.

Features

- Matching with industry standard active fiber geometries 125, 250, 400 µm
- Glass cladding diameter is designed to "fit-in" octagonal active fibers
- Low signal and pump coupling losses from passive to active fiber
- Round cladding for easy cleaving, splicing and handling
- Single cladding fibers feature a dual coated acrylate coating
- Double cladding fibers feature a low-index fluoroacrylate coating with >0.46 NA

Typical device specification

LIEKKI [™] passive fiber	Core	±	Cladding	±	Coating	±	NA	±	Cladding NA, >	Birefringence	Proof test >, kpsi	Matching active LIEKKI [™] fiber
Passive-6/125	5.5	0.5	125	2	245	15	0.15	0.01			100	Yb1200-6/125DC
Passive-6/125DC	5.5	0.5	125	2	245	15	0.15	0.01	0.46		100	Yb1200-6/125DC
Passive-6/125DC-PM	5.5	0.5	125	2	245	15	0.15	0.01	0.46	2.0E-04	100	Yb1200-6/125DC-PM
Passive-10/125	10	1	125	2	245	15	0.08	0.01			100	Yb1200-10/125DC
Passive-10/125DC	10	1	125	2	245	15	0.08	0.01	0.46		100	Yb1200-10/125DC

nLIGHT Corporation • 5408 NE 88th Street • Vancouver, WA 98665 • USA

Tel. +1 360 566 4460 • Fax. +1 360 546 1960 • fibers@nlight.net • www.nlight.net

*n*LIGHT

HIGH-POWER SEMICONDUCTOR LASERS AND FIBERS

Typical device specification

LIEKKI TM passive fiber	Core	±	Cladding	±	Coating	±	NA	±	Cladding NA, >	Birefrin- gence	Proof test >, kpsi	Matching active LIEKKI [™] fiber
Passive-10/125-PM	10	1	125	2	245	15	0.08	0.01				Yb1200-10/125DC-PM
Passive-10/125DC-PM	10	1	125	2	245	15	0.08	0.01	0.46	1.4E-04	100	Yb1200-10/125DC-PM
Passive-12/125	12	1	125	2	245	15	0.07	0.01			100	
Passive-12/125DC	12	1	125	2	245	15	0.07	0.01	0.46		100	
Passive-20/125	20	2	125	2	245	15	0.07	0.01			100	Yb1200-20/125DC
Passive-20/125DC	20	2	125	2	245	15	0.07	0.01	0.46		100	Yb1200-20/125DC
Passive-20/125-PM	20	2	125	2	245	15	0.07	0.01		8.0E-05	100	Yb1200-20/125DC-PM
Passive-20/125DC-PM	20	2	125	2	245	15	0.07	0.01	0.46	8.0E-05	100	Yb1200-20/125DC-PM
Passive-20/400	20	2	400	8	500	15	0.07	0.01			50	Yb1200-20/400DC
Passive-20/400DC	20	2	400	8	500	15	0.07	0.01	0.46		50	Yb1200-20/400DC
Passive-20/400-PM	20	2	400	8	500	15	0.07	0.01		1.6E-04	50	Yb1200-20/400DC-PM
Passive-20/400DC-PM	20	2	400	8	500	15	0.07	0.01	0.46	1.6E-04	50	Yb1200-20/400DC-PM
Passive-20/400/460DC, All-glass	20	2	400	8	580	15	0.07	0.01	0.22		50	
Passive-25/250	25	2.5	250	5	350	15	0.07	0.01			100	Yb1200-25/250DC
Passive-25/250DC	25	2.5	250	5	350	15	0.07	0.01	0.46		100	Yb1200-25/250DC
Passive-25/250DC-PM	25	2.5	250	5	350	15	0.07	0.01	0.46	1.6E-04	100	Yb1200-25/250DC-PM
Passive-30/250	30	3	250	5	350	15	0.07	0.01			100	Yb1200-30/250DC
Passive-30/250DC	30	3	250	5	350	15	0.07	0.01	0.46		100	Yb1200-30/250DC
Passive-30/250DC-PM	30	3	250	5	350	15	0.07	0.01	0.46	1.6E-04	100	Yb1200-30/250DC-PM

Notice

nLIGHT continually improves its products to provide its customers with outstanding quality and reliability. nLIGHT may make changes to specifications and product descriptions at any time, without notice. In addition, nLIGHT offers a limited warranty to ensure customer satisfaction. For complete details, please contact your nLIGHT sales representative.