

# **LIEKKI<sup>TM</sup> Yb1200-25/250**



# **Large Mode Area Ytterbium Doped Fiber**

LIEKKI<sup>TM</sup> Yb1200-25/250 fibers are highly doped fibers which feature very high cladding absorption, high efficiency per application length and excellent beam quality. They are ideal fibers for high average power pulsed fiber amplifiers.

LIEKKI<sup>TM</sup> Yb1200-25/250 fibers are available as double cladding (Yb1200-25/250DC) and double cladding polarization maintaining (Yb1200-25/250DC-PM) fibers.

## **Applications**

- High average power pulsed amplifiers
- Materials processing
- LIDAR
- Range finding

#### **Features**

- Very high cladding absorption
- Large, low NA core
- Low non-linearities
- Low photodarkening
- Excellent beam quality

### Typical device specification


		LIEKKI <sup>TM</sup> Yb1200-25/250DC	LIEKKI <sup>™</sup> Yb1200-25/250DC-PM
Optical			
Peak cladding absorption at 976 nm (nominal)	dB/m	(10.8)	(11.2)
Cladding absorption at 920 nm	dB/m	$2.5 \pm 0.7$	$2.6 \pm 0.7$
Core numerical aperture		$0.07 \pm 0.01$	$0.07 \pm 0.01$
Birefringence			> 1.4E-04
Geometrical and mechanical			
Core diameter	μm	25 ± 2.5	25 ± 2.5
Core concentricity error	μm	< 1.5	< 1.5
Cladding diameter	μm	250 ± 15	$250 \pm 15$
Cladding geometry		octagonal	round
Coating diameter	μm	$350 \pm 15$	$350 \pm 15$
Coating material		low index acrylate	low index acrylate
Cladding numerical aperture		> 0.46	> 0.46
Proof test	kpsi	> 100	> 100




#### HIGH-POWER SEMICONDUCTOR LASERS AND FIBERS

#### Typical performance data

Typical performance data for Yb1200-25/250DC



#### Typical performance data for Yb1200-25/250DC-PM



#### Notice

nLIGHT continually improves its products to provide its customers with outstanding quality and reliability. nLIGHT may make changes to specifications and product descriptions at any time, without notice. In addition, nLIGHT offers a limited warranty to ensure customer satisfaction. For complete details, please contact your nLIGHT sales representative.